

Properties

Description

European corrected grain, aniline dyed through, pigmented & tipped leather. Available in 6 stock colours.

Attributes

Chrome tanned raw hides, with a characterful grain.

Hide Size

5.5m² / 59ft²

Thickness

1.5mm +/- 0.1mm

Weight

840gsm +/- 10g

Grain Characteristics

Uniform

Finish Characteristics

Pigmented, Hand-tipped.

Test Performance

Test	Test Method	Performance
Tear resistance	UNI EN ISO 3377-1	> = 20
Adhesion of finishing	UNI EN ISO 11644	> = 2 N/10mm
Flex resistance - 50'000 cycles	UNI EN ISO 5402	No cracks
Light Fastness	UNI EN ISO 105-B02	> = 6 / Blue Scale
Dry Rub Fastness - 1000 cycles	UNI EN ISO 11640	> = 4 / Grey Scale
Wet Rub Fastness - 250 cycles	UNI EN ISO 11640	> = 4 / Grey Scale
Alkaline perspiration rub fastness - 80 cycles	UNI EN ISO 11640	> = 4 / Grey Scale

Flammability

Test	Test Method	Performance
Cigarette test - Match test	UNI EN 1021-1 - UNI EN 1021-2	Complies
Cigarette Ignition Resistance	NFPA 260/UFAC	Complies
FS191 Method 5903-Port Authority of New York & New Jersey		On demand
IMO Resolution A.652 (16)		Complies
California TB 117 Section E		Complies

Our leather is processed in conformity with REACH regulation.

Durability, Cleaning & Maintenance

Excellent. Recommended for all upholstery applications.

- Avoid placing leather in direct sunlight
- Keep the leather away from direct heat
- Dust regularly with a clean, soft, dry cloth
- Spots can be cleaned with a lightly damp cloth and mild soap
- Dry immediately after the treatment
- Do not rub. Use a light circular motion working toward the centre of the stain

Certifications



UNI 11239



ISO 14025



ISO 14067/CD2



RAL-UZ 148



RAL-GZ 430